

POLYLUB GLY 791

Special synthetic lubricating grease for plain bearings subject to high loads and temperatures



Benefits for your application

- For metal/metal and plastic/steel material pairings
- Neutral towards many plastics and elastomers
- Provides good wear protection to fibre-reinforced plastics
- Good corrosion protection of metal mating surfaces

Description

POLYLUB GLY 791 is based on a synthetic hydrocarbon oil, mineral oil and special lithium soap. It has been designed for friction reduction and wear protection of plain bearings and slideways with metal/metal or plastic/metal material pairings.

This special lubricant covers a wide range of operating conditions, from low to high speeds and loads, even in the case of fibre-reinforced plastic components and metal/plastic sliding pairings.

The lubrication of plastics is special in a number of ways. As the behaviour of metals and plastics differs in many aspects, the lubricant's properties have to be adjusted to the plastic. Compared to many metals, plastics are relatively soft. Solid lubricants, which may achieve a positive effect on many metal friction points, can have a negative or no effect at all on plastic lube points. With the formulation of POLYLUB 791, Klüber Lubrication offers a product which is free of solid lubricant, but covers the many operating conditions mentioned above.

Owing to the many different plastic compositions, however, we recommend checking their compatibility particularly prior to series application.

Slideways, plain bearings:

For many types of plain bearing designs.

POLYLUB GLY 791 prevents stick-slip to a large extent, particularly in applications where normally a hydrodynamic film cannot form.

Owing to the good damping properties, noise and cracking is considerably reduced.

Application notes

POLYLUB GLY 791 is applied by brush, spatula or automatic metering systems. The use of central lubrication systems is possible in principle but should be checked in each individual case.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Application

Vehicles:

Seat mechanisms, shock absorbers

Pack sizes	POLYLUB GLY 791
Can 1 kg	+
Bucket 25 kg	+

Product data	POLYLUB GLY 791
Article number	020206
NLGI grade, DIN 51818	1
Lower service temperature	-40 °C / -40 °F
Upper service temperature	150 °C / 302 °F



POLYLUB GLY 791

Special synthetic lubricating grease for plain bearings subject to high loads and temperatures

Product data	POLYLUB GLY 791
Colour space	orange
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	310 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	340 x 0.1 mm
Shear viscosity at 25°C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, upper limit value	9 000 mPas
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, lower limit value	6 500 mPas
Corrosion inhibiting properties of lubricating greases, DIN 51802, (SKF-EMCOR), test duration: 1 week, distilled water	<= 1 corrosion degree
Drop point, DIN ISO 2176, IP 396	>= 230 °C
Oil separation, based on ASTM D 6184 [FTMS 791 C 321] after 30 h/150 °C	<= 9 % by weight
Four-ball tester, wear factor, DIN 51350 pt. 05, 1 h/400 N, wear scar diameter	<= 0.9 mm
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.