



Consumer Solutions

XIAMETER™ Brand Sealant Formulation Materials

Product Technical Data/Selection Guide (Korea)

Make the XIAMETER™ brand your one-stop shop for the materials you need to formulate your sealants.

Visit www.xiameter.com to learn more about the many product options available to you from the XIAMETER™ brand.

XIAMETER™
silicones simplified by

Polymers							
Product Name	Description	Viscosity	Shelf Life	Silanol Content	Specific Gravity @ 25°	Packaging	Material #
XIAMETER™ OHX-4061 Polymer, 20,000 cSt	100% water-clear silicone fluid polymer can be used as an intermediate for silicone-based sealant manufacturing	20,000 cSt	1,800 days	0.07%	0.98	200 kg drum/ 900 kg IBC	4022439/ 4026325
XIAMETER™ OHX-4071 Polymer, 50,000 cSt	100% water-clear silicone fluid polymer; can be used as an intermediate for silicone-based sealant manufacturing; essentially odorless	50,000 cSt	1,800 days	0.04%	0.98	195 kg drum/ 900 kg IBC	4022475/ 4040720
XIAMETER™ OHX-4081 Polymer, 80,000 cSt	Polydimethylsiloxane polymer with terminated, curable silanol functionality	80,000 cSt	720 days	0.0325%	0.975	195 kg drum/ 900 kg IBC	4022471/ 4022472

Fluids and Cyclics							
Product Name	Description	Viscosity	Shelf Life	Flash Point Closed Cup.	Specific Gravity @ 25°	Packaging	Material #
XIAMETER™ PMX-200 Silicone Fluid, 100 cSt	100% active polydimethylsiloxane polymer	100 cSt	1,080 days	> 100°C	0.96	200 kg drum	4088892
XIAMETER™ PMX-200 Silicone Fluid, 1,000 cSt	100% active polydimethylsiloxane polymer	1,000 cSt	1,080 days	> 100°C	0.971	200 kg drum	4088895

Silanes							
Product Name	Description	Viscosity	Shelf Life	Flash Point Closed Cup.	Specific Gravity @ 25°	Packaging	Material #
XIAMETER™ OFS-1579 Silane	An acetoxysilane used as a crosslinker for acetoxysilane-cure silicone RTV sealants	2 cSt	720 days	82°C	1.1	220 kg drum	4022740
XIAMETER™ OFS-6020 Silane	Aminoethylaminopropyltrimethoxysilane – $\text{H}_2\text{NC}_2\text{H}_4\text{NHC}_3\text{H}_6\text{-Si}(\text{OCH}_3)_3$ coupling agent for many thermoset and thermoplastic resins with glass or mineral fillers	5 cSt	1,080 days	85°C	1.03	205 kg drum/ 1,025 kg IBC	4022790/ 4022789

HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent. Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

© 2018 The Dow Chemical Company. All rights reserved.

30023848

Form No. 95-735-01 A