

## ARALDITE® AW 9102 CI / HW 9102 CI

### Product Description

ARALDITE® AW 9102 CI /HW 9102 CI is a multipurpose, two component, room temperature curing adhesive of high strength and toughness. It is suitable for bonding a wide variety of metal, aluminum honeycomb, ceramics, sandstone, fireproof panel and most other materials in common use. It is a versatile adhesive for the floor, roof, barrier wall in transportation as well as most honeycomb curtain wall application.

### Features

- Multi-purpose & bonds a wide variety of materials in common use
- Long work life
- Low shrinkage
- Good heat resistance
- EN45545-2: 2013: R1 / HL3

### Typical Properties

Property	ARALDITE® AW 9102 CI	ARALDITE® HW 9102 CI	Mixed System
Appearance	Pale	Pale Yellow	Pale Yellow
Density, g/cm <sup>3</sup>	ca. 1.41	ca. 1.2	ca. 1.33
Viscosity @ 25°C, cP	10,000 - 17,000	8,000 – 16,000	8,000-20,000
Pot Life @ 25°C, 100 g, min	--	--	ca. 80

\*Properties are based on Huntsman test methods. Copies are available upon request

### Processing

#### Mix ratio

Product	Parts by weight	Parts by volume
ARALDITE® AW 9102 CI	100	100
ARALDITE® HW 9102 CI	40	47

### Pretreatment

The strength and durability of a bonded joint are dependent on proper treatment of the surfaces to be bonded. At the very least, joint surfaces should be cleaned with a good degreasing agent such as acetone, iso-propanol (for plastics) or other proprietary degreasing agents in order to remove all traces of oil, grease and dirt. Low grade alcohol, gasoline (petrol) or paint thinners should never be used. The strongest and most durable joints are obtained by either mechanically abrading or chemically etching (“pickling”) the degreased surfaces. Abrading should be followed by a second degreasing treatment.

### Application of adhesive

The resin/hardener mix may be applied manually or robotically to the pre-treated and dry joint surfaces. Huntsman's technical support group can assist the user in the selection of a suitable application method as well as suggest a variety of reputable companies that manufacture and service adhesive dispensing equipment. A layer of adhesive 0.05 to 0.10 mm thick will normally impart the greatest lap shear strength to the joint. Huntsman stresses that proper adhesive joint design is also critical for a durable bond. The joint components should be assembled and secured in a fixed position as soon as the adhesive has been applied. For more detailed explanations regarding surface preparation and pre-treatment, adhesive joint design, and the dual syringe dispensing system, visit [www.araldite2000plus.com](http://www.araldite2000plus.com).

### Equipment Maintenance

All tools should be cleaned with hot water and soap before adhesives residues have had time to cure. The removal of cured residues is a difficult and time-consuming operation. If solvents such as acetone are used for cleaning, operatives should take the appropriate precautions and, in addition, avoid skin and eye contact.

## Typical Physical Properties

Unless otherwise stated, the figures given below were all determined by testing standard specimens made by lap jointing 4.5 x 1 x 0.063 in (114 x 25 x 1.6 mm) strips of aluminum alloy. The joint area was 0.5 x 1 in (12.5 x 25 mm) in each case.

The figures were determined with typical production batches using standard testing methods. They are provided solely as technical information and do not constitute a product specification.

Samples were cured at 158 °F (70 °C) for 2 hours and tested at 73 °F, unless otherwise stated.

Property	Value	Test Method
Lap shear strength, aluminum, psi	2900	ISO 4587
Lap shear strength, 45# steel, psi	3625	ISO 4587
Roll peel test, N*mm/mm	45	ASTM D1781-98
Glass transition temperature, DSC, T <sub>g</sub> , °F	ca. 125	Huntsman
Plane tensile strength, psi	507	GB/T 1452
T-peel strength, N/mm	3.5	ISO 11339

## Storage

**ARALDITE® AW 9102 CI and HW 9102 CI** should be stored in a dry place, in its sealed original container, at room temperature and the components must be stored in sealed containers. The expiry date is indicated on the label.

## Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

### First Aid!

Refer to SDS as mentioned above.

**KEEP OUT OF REACH OF CHILDREN**

**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

### Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas LLC, or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman, if any.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

**ARALDITE®** is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

© 2021 Huntsman Advanced Materials Inc.

#### Main Offices:

**Huntsman Corporation**  
10003 Woodloch Forest Dr  
The Woodlands, TX 77380  
888-564-9318

**Huntsman Advanced Technology Center**  
8600 Gosling Rd.  
The Woodlands, TX 77381  
281-719-7400